

## PRODUCT DATA SHEET

# SikaBiresin® UR404 / SikaBiresin® UR419 (Biresin® U1404 / Biresin® U1419)

## ELASTOMERIC CASTING RESIN FOR MOULD MAKING

### APPLICATIONS

- Casting of flexible moulds
- Manufacture of elastic, flexible mouldings and components

### MAIN PROPERTIES

- Insensitive to moisture
- Good tensile strength and elasticity
- Dyeable with **SikaBiresin® Colour Paste**

### DESCRIPTION

Basis	Two component polyurethane system
Component A	<b>SikaBiresin® UR404</b> , isocyanate prepolymer, colourless-transparent
Component B	<b>SikaBiresin® UR419</b> , amine, brownish-transparent

### PHYSICAL PROPERTIES

		Isocyanate (A)	Amine (B)
Components		<b>SikaBiresin® UR404</b>	<b>SikaBiresin® UR419</b>
Viscosity, 25 °C	mPa.s	~ 6,500	~ 200
Density	g/cm <sup>3</sup>	1.03	1.02
Mixing ratio A:B	in parts by weight	100	9
		Mixture	
Colour		brownish-transparent*	
Pot life, room temperature, 500 g	sec	~ 130	
Curing time	d	5 – 7	

\* dependent on raw materials the colour can differ without changing the mechanical properties

## MECHANICAL PROPERTIES

approx. values

Density	ISO 1183	g/cm <sup>3</sup>	1.1
Shore hardness	ISO 868	-	A 81
Tensile strength	ISO 527	MPa	17
Elongation at break	ISO 527	%	> 630
Tear strength	ISO 34	N/mm	26

## PACKAGING UNITS

- |   |                             |
|---|-----------------------------|
| ■ Isocyanate (A), <b>SikaBiresin® UR404</b> | 200 kg; 20 kg; 8 kg; 0.8 kg |
| ■ Amine (B), <b>SikaBiresin® UR419</b>      | 16 kg; 1.6; 6 x 0.16 kg     |

## PROCESSING DATA

- The material, processing and mould temperature must be at least 18 – 25 °C.
- When using pigments, it is recommended to add max. 1% of SikaBiresin® Colour Paste.
- Add the pigments prior to processing to component B.
- Both components have to be mixed thoroughly according to mixing ratio and poured immediately into the released mould with beginning at the lowest point.
- Porous surfaces have to be well sealed previously.
- If using wood (e. g. laminated wood) as supporting cores or PUR foam plates with low to middle density, a previous sealing is necessary.
- The compatibility of the sealing on PUR foam has to be tested separately.
- Recommended release agents are Sika® Liquid Wax-815, Sika® Liquid Wax-852, Sika® Liquid Wax-872 or Sika® Pasty Wax-818. For more information, see Product Data Sheets of the release agents.
- Pay attention to dry conditions and dry mould surfaces while processing.

## STORAGE CONDITIONS

Shelf life	■ Isocyanate (A), <b>SikaBiresin® UR404</b>	12 months
	■ Amine (B), <b>SikaBiresin® UR419</b>	12 months
Storage temperature	■ Isocyanate (A), <b>SikaBiresin® UR404</b>	18 – 25 °C
	■ Amine (B), <b>SikaBiresin® UR419</b>	18 – 25 °C
Crystallization	■ After prolonged storage at low temperature, crystallization of components may occur.	
	■ This is easily removed by warming up for a sufficient time to a maximum of 70 °C.	
	■ Allow to cool to requested processing temperature before use.	
Opened packagings	■ Containers must be closed tightly immediately after use to prevent moisture ingress.	
	■ The residual material needs to be used up as soon as possible.	

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Advanced Resins. Copies of the following publications are available on request: Safety Data Sheets

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and end use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

---

## Contact

---

### SIKA DEUTSCHLAND GMBH

Business Unit Industrie  
Stuttgarter Straße 139  
72574 Bad Urach  
Phone: +49 7125 940-7692  
E-Mail: [industry@de.sika.com](mailto:industry@de.sika.com)  
Website: [www.sika.de](http://www.sika.de)

### SIKA AUTOMOTIVE FRANCE S.A.S.

ZI des Béthunes - 15, Rue de l'Équerre  
95310 Saint-Ouen-l'Aumône  
CS 40444  
95005 Cergy Pontoise Cedex - FRANCE  
Phone: +33 1 34 40 34 60  
Fax: +33 1 34 21 97 87  
E-Mail: [advanced.resins@fr.sika.com](mailto:advanced.resins@fr.sika.com)  
Website: [www.sikaadvancedresins.fr](http://www.sikaadvancedresins.fr)

### AXSON TECHNOLOGIES SPAIN, S.L. –

Sika Advanced Resins  
C/Guardaagullés, 8 – P.I. Congost - 08520  
Les Franqueses del Valles (Barcelona) - SPAIN  
Phone: +34 93 225 16 20  
Fax: +34 93 225 03 05  
E-Mail: [sar-sales@es.sika.com](mailto:sar-sales@es.sika.com)  
Website: [www.sikaadvancedresins.es](http://www.sikaadvancedresins.es)

### AXSON ITALIA S.R.L. – Sika Advanced Resins

Via Morandi 15  
21047 Saronno (Va) – ITALY  
Phone: +39 02 96 70 23 36  
Fax: +39 02 96 70 23 69  
E-Mail: [axson@axson.it](mailto:axson@axson.it)  
Website: [www.sikaadvancedresins.it](http://www.sikaadvancedresins.it)

### AXSON UK LTD – Sika Advanced Resins

Unit 15 Studlands Park Ind. Estate  
Newmarket Suffolk, CB8 7AU - UNITED KINGDOM  
Phone: +44 1638 660 062  
Fax: +44 1638 665 078  
E-Mail: [sales.uk@axson.com](mailto:sales.uk@axson.com)  
Website: [www.sikaadvancedresins.uk](http://www.sikaadvancedresins.uk)

### SIKA AUTOMOTIVE SLOVAKIA S.R.O.

Tovarenska 49  
953 01 Zlate Moravce - SLOVAKIA  
Phone: +421 2 5727 29 33  
Fax: +421 37 3000 087  
E-Mail: [SikaAdvancedResins@sk.sika.com](mailto:SikaAdvancedResins@sk.sika.com)  
Website: [www.sikaadvancedresins.com](http://www.sikaadvancedresins.com)

### SIKA ADVANCED RESINS US

30800 Stephenson Highway  
Madison Heights, Michigan 48071 - USA  
Phone: +1 248 588 2270  
Fax: +1 248 616 7452  
E-Mail: [advanced.resins@us.sika.com](mailto:advanced.resins@us.sika.com)  
Website: [www.sikaadvancedresins.us](http://www.sikaadvancedresins.us)

### SIKA AUTOMOTIVE EATON RAPIDS, INC.

1611 Hults Drive  
Eaton Rapids, Michigan 48827 - USA  
Phone: +1 517 663 81 91  
Fax: +1 517 663 05 23  
E-Mail: [advanced.resins@us.sika.com](mailto:advanced.resins@us.sika.com)  
Website: [www.sikaadvancedresins.us](http://www.sikaadvancedresins.us)

### SIKA MEXICANA SA de CV

Av. Gustavo Baz #309 Centrum Park  
54060 Tlanepantla Estado de MEXICO  
Phone: +52 442 238 5800  
E-Mail: [roman.octavio@mx.sika.com](mailto:roman.octavio@mx.sika.com)

### SIKA AUTOMOTIVE SHANGHAI CO. LTD.

N°53 Tai Gu Road  
Wai Gao Qiao  
Free Trade Zone, Pudong  
200131 Shanghai - CHINA  
Phone: +86 21 58 68 30 37  
Fax: +86 21 58 68 26 01  
E-Mail: [marketing.china@axson.com](mailto:marketing.china@axson.com)  
Website: [www.sikaaxson.cn](http://www.sikaaxson.cn)

### Sika Ltd.

10 F, Shinagawa Intercity Tower B.  
2-15-2 Konan, Minato-ku  
Tokyo 108-6110 - JAPAN  
Phone: +81 3 6433 2314  
Fax: +81 3 6433 2102  
E-Mail: [advanced-resins@jp.sika.com](mailto:advanced-resins@jp.sika.com)  
Website: [www.jpn.sika.com](http://www.jpn.sika.com)

### SIKA INDIA PVT LTD,

Plot No. Pap-V-90/1,  
Chakan Industrial Area,  
Phase-II, Vasuli, Khed, PUNE,  
Maharashtra – 410501  
E-Mail: [info.india@in.sika.com](mailto:info.india@in.sika.com)

---

## PRODUCT DATA SHEET

SikaBiresin® UR404 / SikaBiresin® UR419

(Biresin® U1404 / Biresin® U1419)

Oktober 2020, Version 01

Sika Advanced Resins