

PRODUCT DATA SHEET

SikaBiresin[®] UR530 / UR503 (UR 58300 / UR 5803)

POLYURETHANE CASTING ELASTOMER – SHORE A 30 – POT LIFE 15-20'

APPLICATIONS

- PU elastomer designed to make moulds for concrete industry by hand casting or with the help of a 2-component low pressure machine

MAIN PROPERTIES

- High elongation at break
- Solvent and mercury free
- Chemical stability

DESCRIPTION

Basis	Two component polyurethane system
Component A	SikaBiresin[®] UR503 , isocyanate, amber
Component B	SikaBiresin[®] UR530 , polyol, beige

PHYSICAL PROPERTIES

		Isocyanate (A)	Polyol (B)
Components		SikaBiresin[®] UR503	SikaBiresin[®] UR530
Viscosity, 25 °C	mPa.s	~ 2,000	~ 6,900
Density, 25 °C	g/cm ³	1.16	1.37
Mixing ratio A:B	in parts by weight	10	100
		Mixture	
Colour		Beige	
Viscosity, 25 °C	mPa.s	~ 4,000	
Pot life, 25 °C, 165 g	min	15 – 20	
Demoulding time at 23 °C	h	~ 24	
Curing time at 23 °C	h	~ 120	
Maximal casting thickness	mm	~ 80	

MECHANICAL PROPERTIES

approx. values

Density	ISO 2781	g/cm ³	1.35
Shore hardness	ISO 868	Shore A1	A 30
Tensile strength	ISO 37	MPa	1.55
Tear strength	ISO 34	kN/m	6
Elongation at break	ISO 37	%	900
Abrasion resistance (TABER)	ISO 5470	mm ³ / 100U	120

THERMAL AND SPECIFIC PROPERTIES

approx. values

Glass transition temperature	ISO 11357	°C	< 0
------------------------------	-----------	----	-----

PACKAGING UNITS

- | | |
|---|--------------------------|
| ■ Isocyanate (A), SikaBiresin® UR503 | 227.5 kg / 5 kg / 2.5 kg |
| ■ Polyol (B), SikaBiresin® UR530 | 25 kg |

PROCESSING DATA

- The material, processing and master-model temperature must be at least 18 – 25 °C.
- If master-model surface is porous it must be sealed prior applying release agent.
- Recommended release agents are was based. For more information, and recommendation see Product Data Sheets of Sika Release agents or contact local technical assistance.
- When using pigments, it is recommended to add max 1% of SikaBiresin® Color Paste. Add the pigment in component B and stir to homogenize prior mixing with component A.
- Both components have to be mixed thoroughly with a spatula or low-rpm stirrer according to mixing ratio.
- To secure homogeneous and complete mixing, fill the mixture in a second empty container and mix again briefly. Then pour immediately starting from the deepest point.
- Demolding time may vary depending on casted thickness and room temperature. Refer to the table above or please check in your own conditions.
- To achieve the highest performance, leave the elastomeric mould at 23 °C for 5 days before using it.
- To favor concrete mould longevity we invite you to check compatibility of your local release agent for concrete or contact our local technical support.
- In case of use with a 2-component low-pressure machine please make sure with machine supplier about its appropriateness, accuracy and maintenance.

STORAGE CONDITIONS

Shelf life	■ Isocyanate (A), SikaBiresin® UR503	6 months
	■ Polyol (B), SikaBiresin® UR530	12 months
Storage temperature	■ Isocyanate (A), SikaBiresin® UR503	18 – 25 °C
	■ Polyol (B), SikaBiresin® UR530	18 – 25 °C
Crystallization	■ After prolonged storage at low temperature, crystallization of components may occur.	
	■ This is easily removed by warming up for a sufficient time to a maximum of 70 °C.	
	■ Allow to cool to requested processing temperature before use.	

PRODUCT DATA SHEET

SikaBiresin® UR530 / UR503 (UR 58300 / UR 5803)

June 2021, Version 01

Sika Advanced Resins

2

BUILDING TRUST



Opened packagings

- Containers must be closed tightly immediately after use to prevent moisture ingress.
- The residual material needs to be used up as soon as possible.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Advanced Resins. Copies of the following publications are available on request: Safety Data Sheets

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and end use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Contact

SIKA DEUTSCHLAND GMBH

Business Unit Industry
Stuttgarter Straße 139
72574 Bad Urach
Phone: +49 7125 940-7692
E-Mail: industry@de.sika.com
Website: www.sika.de

SIKA AUTOMOTIVE FRANCE S.A.S.

ZI des Béthunes - 15, Rue de l'Equerre
95310 Saint-Ouen-l'Aumône
CS 40444
95005 Cergy Pontoise Cedex - FRANCE
Phone: +33 1 34 40 34 60
Fax: +33 1 34 21 97 87
E-Mail: advanced.resins@fr.sika.com
Website: www.sikaadvancedresins.fr

Sika S.A.U.

Carretera de Madrid a Irún – km 14.5
P.I. Congost 28108 Alcobendas (Madrid) - SPAIN
Phone: +34 93 225 16 20
E-Mail: sar-sales@es.sika.com
Website: www.sikaadvancedresins.es

Sika Italia S.p.A.

Via Luigi Einaudi 6
20068 Peschiera Borromeo (MI) - Italy
Phone: +39 02 54778111
Fax: +39 02 54778 119
E-Mail: info@sika.it
Website: www.sika.it

Sika Limited

Head Office, Watchmead – Welwyn
Garden City – AL7 1BQ – United Kingdom
Phone: +44 1707 394444
E-Mail: industry-sales@uk.sika.com
Website: www.gbr.sika.com

SIKA AUTOMOTIVE SLOVAKIA S.R.O.

Tovarenska 49
953 01 Zlate Moravce - SLOVAKIA
Phone: +421 2 5727 29 33
Fax: +421 37 3000 087
E-Mail: SikaAdvancedResins@sk.sika.com
Website: www.sikaadvancedresins.com

Sika Industry – Tooling, Resins and Marine

30800 Stephenson Highway
Madison Heights, Michigan 48071 - USA
Phone: +1 248 588 2270
Fax: +1 248 616 7452
E-Mail: advanced.resins@us.sika.com
Website: www.sikaindustry.com

SIKA AUTOMOTIVE EATON RAPIDS, INC.

1611 Hults Drive
Eaton Rapids, Michigan 48827 - USA
Phone: +1 517 663 81 91
Fax: +1 517 663 05 23
E-Mail: advanced.resins@us.sika.com
Website: www.sikaadvancedresins.us

SIKA MEXICANA SA de CV

Av. Gustavo Baz #309 Centrum Park
54060 Tlanepantla Estado de MEXICO
Phone: +52 442 238 5800
E-Mail: roman.octavio@mx.sika.com

SIKA AUTOMOTIVE SHANGHAI CO. LTD.

N°53 Tai Gu Road
Wai Gao Qiao
Free Trade Zone, Pudong
200131 Shanghai - CHINA
Phone: +86 21 58 68 30 37
Fax: +86 21 58 68 26 01
E-Mail: industry@cn.sika.com
Website: www.sika.cn

Sika Ltd.

10 F, Shinagawa Intercity Tower B.
2-15-2 Konan, Minato-ku
Tokyo 108-6110 - JAPAN
Phone: +81 3 6433 2314
Fax: +81 3 6433 2102
E-Mail: advanced-resins@jp.sika.com
Website: www.jpn.sika.com

SIKA INDIA PVT LTD,

Plot No. Pap-V-90/1,
Chakan Industrial Area,
Phase-II, Vasuli, Khed, PUNE,
Maharashtra – 410501
E-Mail: info.india@in.sika.com

PRODUCT DATA SHEET

SikaBiresin® UR530 / UR503 (UR 58300 /
UR 5803)

June 2021, Version 01

Sika Advanced Resins